


ARONIX[®] M-6250

Polyester acrylate(bifunctional)

Chemical structure



Polyester acrylate(bifunctional)

Description

Molecular Weight: trade secret

Functionality: 2

Appearance: Liquid

Product data

Color (APHA)	< 300
Viscosity (mPa·s/25°C)	300~700
Residual (%)	<0.1
Acid value (mgKOH/g)	< 1.0
Relative density (/°C)	1.215/25
Surface tension (mN/m)	45.5
Reflective index (n _D 25)	1.510

Features

- Low viscosity
- Low skin irritation

Application

- Coating
- Adhesive
- Ink
- Optical materials

Safety data

P.I.I.	2.3
Flash point (°C)	159 Open – cup
Inhibitor as MEHQ (ppm)	350

Properties of cured film

Tensile strength (kg/cm ²)	9.8
Elongation (%)	30
Tg (°C)	45
Relative density (/°C)	1.314/25
Cure shrinkage (%)	7.56
Shore hardness	D85

Registration

Japan (METI)	Listed
USA (TSCA)	Listed
EU (REACH)	Not supported
China (IECSC)	Listed
Korea (ECL)	Listed
K-REACH	Not supported
Taiwan	Listed

Package

18kg C/N
200kg D/M

SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE.