


ARONIX[®] M-8560

Polyester acrylate(multifunctional)

Chemical structure



Polyester acrylate(multifunctional)

Description

Molecular Weight: trade secret

Functionality: 3 and more

Appearance: Liquid

Product data

Color (APHA)	< 300
Viscosity (mPa·s/25°C)	3,400~7,400
Residual (%)	<0.1
Acid value (mgKOH/g)	< 20.0
Relative density (/°C)	-
Surface tension (mN/m)	-
Reflective index (n _D 25)	1.486

Features

- Low skin irritation
- Faster curing than M-8060

Application

- Coating
- Ink
- Adhesive

Safety data

P.I.I.	1.1
Flash point (°C)	160°C(Polymerized) Open – cup
Inhibitor as MEHQ (ppm)	490

Properties of cured film

Tensile strength (kg/cm ²)	51
Elongation (%)	< 1
Tg (°C)	-
Relative density (/°C)	1.260/25
Cure shrinkage (%)	9.83
Shore hardness	D88

Registration

Japan (METI)	Listed
USA (TSCA)	Listed
EU (REACH)	Not supported
China (IECSC)	Listed
Korea (ECL) K-REACH	Listed Not supported
Taiwan	Listed

Package

18kg C/N
200kg D/M

SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE.